

## Cement Based Tile Adhesive [Class C1E (EN 12004)]

### Reference Formula

Raw material	Type	Weight (grams)
Cement	OPC CEM I 42.5 R	33
Filler(silica sand)	0.09 – 0.25 mm	40.1
Filler(silica sand)	0.125 – 0.5 mm	25
Redispersible Polymer Powder	RDP-7053	1
Calcium formate	CaFo-SG98	0.5
Methyl Cellulose	ME-H14N12	0.4
Total		1000
Water requirement	Approximately 240 – 260 g of water per 1 kg of powder	

### Important Notice

This formulation is intended solely for testing purposes. In practical applications, customers must adjust it according to the raw materials used and specific project conditions. Under no circumstances should it be directly employed for production or practical implementation. We shall not be held liable for any project losses arising from customers' independent selection of this formulation for production purposes.

### Contact Info

High-tech zone, Linyi City, China

Sales@sidleychem.com

Techsupport@sidleychem.com